

Saccharin in Electrolytic Nickel Sulfate Baths

INTRODUCTION

Saccharin decreases the tensile strength of electrolytic nickel deposits and can, with increasing concentrations, cause compressive stress. Sulfur can be introduced into the plate from the saccharin when class II nickel brighteners are not present, thus producing deposits with higher tensile strength, higher hardness, and relatively lower ductility. Saccharin, without other nickel brighteners present, produces a cloudy bright plate with relatively low luster.

Determination of saccharin by ion chromatography is faster and has fewer interferences than classical titrimetric methods of analysis. Labor requirements, thus operating costs, are significantly lower with ion chromatography than with classical titrimetric methods. Dionex ion chromatography systems are constructed from inert polymeric materials in the eluent flow path so that an eluent containing 30 mM sulfuric acid can be used and highly corrosive nickel bath samples can be injected directly into the system without corroding system components.

Application areas for saccharin as a class I nickel brightener include:

- Watts Nickel Bath
- Nickel Chloride Bath
- Nickel Chloride-Acetate Bath
- Nickel Fluoroborate Bath
- Hard Nickel Bath
- Nickel Chloride-Sulfate Bath
- Nickel Cobalt Bath
- Nickel Sulfamate Bath

RECOMMENDED EQUIPMENT

Dionex DX 500 Ion Chromatography system consisting of:
 GP40 Gradient Pump with vacuum degassing option
 AD20 Absorbance Detector
 Autosampler
 PeakNet Chromatography Workstation




Figure 1 Saccharin in a new, fresh electrolytic nickel sulfate bath

Now sold under the
 Thermo Scientific brand

Thermo
 SCIENTIFIC

SAMPLE PREPARATION

The sample was diluted to $1/500$ the original concentration with deionized water before direct injection.

SOLUTIONS AND REAGENTS

Eluent 1: 30 mM Sulfuric acid/5% Acetonitrile

Place approximately 500 mL of deionized water in a 1-L volumetric flask. Add 50 mL of HPLC-grade acetonitrile and mix. Add 1.7 mL (3.1 g) concentrated sulfuric acid and mix. Dilute to 1 L with deionized water.

Eluent 2: 30 mM Sulfuric acid/25% Acetonitrile

Place approximately 500 mL of deionized water in a 1-L volumetric flask. Add 250 mL of HPLC-grade acetonitrile and mix. Add 1.7 mL (3.1 g) concentrated sulfuric acid and mix. Dilute to 1 L with deionized water.

Standard: 1000 mg/L Saccharin

Dissolve 1.126 g of sodium saccharin in deionized water. Dilute to 1 L.

CONDITIONS

Column: OmniPac® PAX-500

Eluents: A. 30 mM Sulfuric acid;
5% acetonitrile
B. 30 mM Sulfuric acid;
25% acetonitrile

Flow Rate: 1 mL/min

Inj. Volume: 25 μ L

Detection: UV, 225 nm

Gradient Program:	Time	%A	%B
	0.0	100	0
	20.0	0	100
	30.0	0	100




Figure 2 Saccharin in a working electrolytic nickel sulfate bath

RESULTS AND DISCUSSION

Saccharin, a class I brightener in electrolytic nickel plating baths, was determined in a bright nickel sulfate bath using ion chromatography. The method was linear for injected samples with saccharin in the concentration range between 0.25 mg/L and 250 mg/L. Saccharin was well resolved from other UV-absorbing species present in older working baths. It is recommended that the column be reequilibrated with eluent A for 10 minutes prior to the next run.

OmniPac is a registered trademark of Dionex Corporation.



Printed on recycled and recyclable paper.

Dionex Corporation
1228 Titan Way
P.O. Box 3603
Sunnyvale, CA
94088-3603
(408) 737-0700

Dionex Corporation
Salt Lake City Technical Center
1515 West 2200 South, Suite A
Salt Lake City, UT
84119-1484
(801) 972-9292

Dionex U.S. Regional Offices
Sunnyvale, CA (408) 737-8522
Westmont, IL (630) 789-3660
Smyrna, GA (770) 432-8100
Houston, TX (713) 847-5652
Marlton, NJ (609) 596-0600

Dionex International Subsidiaries
Belgium (015) 203800 Canada (905) 844-9650 France (1) 39 46 08 40 Germany (06126) 991-0 Italy (6) 66030052
Japan (06) 885-1213 The Netherlands (076) 57 14 800 Switzerland (062) 205 99 66 United Kingdom (01276) 691722
* Designed, developed, and manufactured under an NSAI registered ISO 9001 Quality System.
<http://www.dionex.com>



LPN 034621-02 1M 11/96
© 1996 Dionex Corporation