



Linear Calibration Curves for Mixed Columns

Agilent PLgel MIXED Columns

Technical Overview

Introduction

A significant number of GPC applications involve the analysis of polydisperse materials. The modern approach to column selection is to choose PLgel MIXED gel columns where every column contains a mixture of individual pore size materials, accurately blended to cover a specified broad range of molecular weight with a linear calibration to eliminate column mismatch.



Agilent Technologies

Each type of PLgel MIXED gel column is designed for specific types of application, with pore size and particle size distribution matched to the application area. The linear operating range of molecular weight of each PLgel MIXED gel column is illustrated in GPC calibration curves, generated using narrow polystyrene standards.

Conditions

Columns: Every set of data was obtained using a single PLgel MIXED 300 x 7.5 mm column

Eluent: THF

Flow Rate: 1.0 mL/min

Detection: RI




Figure 1. PLgel MIXED gel column GPC calibration curves

www.agilent.com/chem

This information is subject to change without notice.

© Agilent Technologies, Inc. 2010, 2016

Published in UK, June 21, 2016

SI-01749



Agilent Technologies